

H25CHDPEB1

TECHNICAL DATA SHEET



PRODUCT: HEMP BIO-ETHYLENE (HD) 25%

Description: H25CHDPEB1 is comprised of hemp and polyethylene (HDPE) made from renewable raw material. This product is generally used in injection molding, but may be used for other forming methods as developed by individual users. HEMP ETHYLENE is designed to be a drop-in replacement for conventional fossil fuel based polymers.

Natural color us medium brown; pelletized. Refer to molding recommendation below: limiting back pressure and injection speed will allow optimal processing conditions.

Property	Typical Value	Units	Test Method:
Specific Gravity	1.0242	g/cc	ASTM D 792
Tensile Strength @ Break	2,349	psi	ASTM D 638
Tensile Elongation @ Break	9.03	%	ASTM D 638
Flexural Modulus (2% secant)	157,900	psi	ASTM D 790
Melt Flow Index, 230C/2.16Kg	13.94	g/10 min	ASTM D 1238
Izod Impact	0.596	ft. lbs/in	ASTM D 256
Gardner Impact	<20	ft*lbs	ASTM D 5420

GENERAL RECOMMENDATIONS

TEMPERATURES (F)		PRESSURES		OTHER	
Back	270 – 330	Injection	Moderate	Injection Rate:	Moderate
Middle	300 – 340	Hold	Moderate – High	Screw Speed:	Moderate – Fast
Front	300 – 340	Back	Moderate	Pre-drying is recommended before molding to avoid potential for splay	
Nozzle	310 – 370				
Mold	80 - 100				

Data are obtained from tests performed under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

This information serves only as a guideline for processors, users and manufacturers. Due to the complex nature of design and processing, observation on a “trial and error” basis may be required to achieve desired results.

No information supplied by The Hemp Plastic Company (THPC) constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as an approach for investigation for use, based upon THPC or other customer experience. THPC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.